

# Perfection epitomized in marble

## Thassos - Indisputable wonderment and awe. Parakalo!

A light breeze, clear blue skies and a sea the color of which is indescribable. The time here flows slower, everything tastes finer, and the mind saturated with the fresh air absorbs the Mediterranean climate and detects that, which at the first glance is inconspicuous. Magic encapsulated in the tiniest of details.

## Morocco - Shrouded in mystery

Through the mesmerizing, sandy deserts of the Sahara and the bewitching cedar forests of the Middle Atlas, to the spellbinding coastal lagoons. This magical land of the setting sun invites you to come on a fantastic journey, brimming with the Orient, accompanied by an aromatic glass of "the a la menthe" in your hand. A colorful mosaic of oriental cultures.

02



Inspiration

# MARMO

THASSOS / MOROCCO



Inspiration | MARMO THASSOS



”

Thassos – the pearl in Greece's crown became the inspiration for the Marmo Thassos collection – white surfaced tiles with dynamically scattered veins in shades of gray.

*/ Marmo Thassos*



Inspiration | MARMO THASSOS



”

The texture allows for a stunning play of lights, which is sure to splendidly illuminate any design. A palatial interior of a Mediterranean residence in the heart of a native climate? Elegance, that doesn't overwhelm but instead makes the interior feel airy and ethereal?

*/ Marmo Thassos*





”

Regardless of what style you choose, Marmo Thassos will not only guarantee spaciousness, but will emphasize the unique character and extent of that space.






Inspiration | MARMO THASSOS



*/ Marmo Thassos*



*/ Brazilian Quartzite NATURAL*





*/Marmo Thassos*



*/Marmo Morocco*



Inspiration | MARMO THASSOS / MOROCCO






Inspiration | MARMO MOROCCO



”

Inspired by this captivating land, the Marmo Morocco collection is just like the Sahara, shrouded in mystery by day, whilst at night unveiling itself to us in the moonlight. You can lose yourself in it, escape, discover its different faces for years to come.

*/ Marmo Morocco*





”

Mysterious, curious, contrasting,  
with a mystical aura just like the  
culture of Morocco.

*/Marmo Morocco*




*/Modern Concrete SILVER*





MARMO THASSOS | collection

120 x 280




5903313330817 matt  
5903313330916 polished

4 / 0,6



120 x 120



5903313330756 matt  
5903313330855 polished

12 / 0,6


60 x 120



5903313330732 matt  
5903313330831 polished

24 / 0,8

80 x 80



5903313330770 matt  
5903313330879 polished

44 / 0,8

80 x 160



5903313330794 matt  
5903313330893 polished

24 / 0,8

MATT | POLISHED  
PEI ●●●○ /  / (R9) | PEI ●●●●

12 - number of graphic patterns  - textured surface

MARMO MOROCCO | collection

120 x 280




5903313331012 matt  
5903313331111 polished

4 / 0.6



PEI ●●●● / / / / MATT | POLISHED  
PEI ●●●● / / / /


120 x 120



5903313330954 matt  
5903313331050 polished

12 / 0.6


60 x 120



5903313330930 matt  
5903313331036 polished

24 / 0.8


80 x 80



5903313330978 matt  
5903313331074 polished

44 / 0.8

80 x 160



5903313330992 matt  
5903313331098 polished

24 / 0.8



12 - number of graphic patterns   - colour body   - textured surface



## DIMENSIONS AND PACKAGING

	Dimensions [cm]	Pieces in the box	m <sup>2</sup> in the box	Packaging weight [kg]	m <sup>2</sup> / pcs on a pallet	Boxes on a pallet	Pallet weight [kg]	Frost resistance
RECTIFIED TILE	59,7x119,7x0,8	2	1,43	27,31	47,19	33	901,2	✓
	119,7x119,7x0,6	2	2,87	42,60	68,88	24	1022,4	
	79,7x79,7x0,8	2	1,27	24,26	60,96	48	1164,5	
	79,7x159,7x0,8	1	1,27	24,26	50,80	40	970,4	

	Dimensions [cm]	Pieces on a pallet	m <sup>2</sup> on a pallet	Pallet weight [kg]	Pallet dimensions [mm]	Frost resistance
A-FRAME	119,7x279,7x0,6	38	127,3	1980	2900x1479x750	✓
PALLET		25	83,75	1340	3030x1360x380	



This catalogue does not constitute an offer as defined in the Civil Code provisions. The actual appearance of tiles may differ from that presented in the pictures contained herein.













All rights reserved © CERRAD Sp. z o.o. 2022.

HELD CERTIFICATES: compliance with PN-EN 14411:2013-04; for safety  ; EN ISO 9001; EN ISO 14001.

## TECHNICAL PROPERTIES AND STANDARDS

VALUES ACCORDING TO THE STANDARD: PN - EN 14411:2013-04 ANNEX G AND DECLARED – PORCELAIN TILE

	DIMENSIONS AND SURFACE FLATNESS	NOMINAL DIMENSION N	
		7 cm ≤ N < 15	N ≥ 15 cm
tests according to PN-EN ISO 10545-2	length	± 0,9 mm	± 0,6% and max ± 2,0 mm
	width	± 0,9 mm	± 0,6% and max ± 2,0 mm
	thickness	± 0,5 mm	± 5% and max ± 0,5 mm
	deflection from the straight angle	± 0,75 mm	± 0,5% and max ± 2,0 mm
	surface flatness	± 0,75 mm	± 0,5% and max ± 2,0 mm

PN – EN 14411:2013-04 ANNEX G and declared			
	PHYSICAL PROPERTIES	REQUIREMENTS	MEAN VALUE ACHIEVED
	Water absorption, tests according to PN-EN ISO 10545-3	E ≤ 0,5%	0,05% – 0,10%
	Breaking force, tests according to PN-EN ISO 10545-4	for thickness < 7,5 mm – ≥ 700 N for thickness ≥ 7,5 mm – ≥ 1300 N	1300-1500 N 2000-2200 N
	Flexural strength, tests according to PN-EN ISO 10545-4	> 35 N/mm <sup>2</sup>	40-50 N/mm <sup>2</sup>
	Abrasion resistance, tests according to PN-EN ISO 10545-7	according to the manufacturer's declaration	cl. 3 – 4
	Frost resistance, tests according to PN-EN ISO 10545-12	required	resistant
	Chemical resistance, tests according to PN-EN ISO 10545-13, – to acids and bases of low concentration, – to acids and bases of high concentration, – to household agents/water pool salts	according to the manufacturer's classification – min. B	– LA – HA – A
	Non-slip qualities, tests according to DIN 51130 + complementary procedures	according to the manufacturer's declaration	smooth and rustic surface – R9
	Release of lead and cadmium PN-EN ISO 10545-15	requirements of the Commission directive 2005/31/EC ≤ 0,2 mg/l for lead ≤ 0,02 mg/l for cadmium	Lead < 0,1 mg/dm <sup>3</sup> Cadmium < 0,02 mg/dm <sup>3</sup>
	Natural radioactivity ITB 455/2010	no requirements	below regulatory safety limits
	Resistance to staining PN-EN ISO 10545-14	min. 3 cl. (GL)	cl. 5
	Crazing resistance, tests according to PN-EN ISO 10545-11	required	resistant
	Thermal shock resistance, test according to PN-EN ISO 10545-9	required	resistant